

TEST REPORT

No.: SDFTS25008205R02_EN

Date: Jan 13,2026

Page 1 of 3

PDS GROUP AUSTRALIA PTY LTD

20 WRIGHT PI, ALGESTER QLD

Sample Description : COMPOSITE WALL PANEL

Product Specification : VARY SIZES

The above sample(s) data and information was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion arising therefrom. Results apply to the sample as received.

SGS Ref. No. : SZIN2512003424PL02

Sample Receiving Date : Dec 23,2025

Testing Period : Dec 23,2025 to Jan 06,2026

Test Required : AS 5637.1:2015 Determination of fire hazard properties Part 1: Wall and ceiling linings, Prediction

And the test method was according to AS/NZS 3837:1998 + A1:2012 (R2016) Method of Test for Heat and Smoke Release Rates for Materials and Products Using an Oxygen Consumption Calorimeter.

Test result(s) : See attached sheet

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Shunde Branch

Ada

Ada Liu
Approved signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300

t (86-757) 22805888

www.sgsgroup.com.cn

中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888

sgs.china@sgs.com

I. Sample details

Sample description	Panel
Thickness	7.8 mm
Density	7.28 kg/m ²
Test face	Any surface

II. Test conducted

The fire test was conducted in accordance with AS/NZS 3837:1998+A1:2012(R2016) Method of Test for Heat and Smoke Release Rates for Materials and Products Using an Oxygen Consumption Calorimeter.

III. Test Result

To determine a group number of a material by prediction, the material was tested to AS/NZS 3837, and the prediction results as follows:

	1	2	3
Step 1: Determine time to 50 kW/m ² (t ₅₀)/s	30.6	33.6	30.5
Step 2: Calculate the ignitability index (I _{ig})	1.963	1.788	1.966
Step 3: Calculate the two HRR indices	I _{Q1}	7507.6	9534.8
	I _{Q2}	1531.0	1618.4
Step 4: Calculate the following three integral limits	I _{Q,10min}	5740	5835
	I _{Q,2min}	2151	2180
	I _{Q,12min}	1326	1355
Group Number	3	3	3

IV. Conclusion

According to predicted flashover times requirements, the sample assigned as **Group Number 3**.

Average specific extinction area (ASEA) = 478.5 m²/ kg



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300

t (86-757) 22805888

www.sgs.com.cn

中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888

sgs.china@sgs.com


Predicted flashover times requirements (According to AS 5637.1:2015 clause 8)

Integral limits	Predicted flashover time for each replicate	Group number
$I_{Q1} > I_{Q,10min}$ and $I_{Q2} > I_{Q,2min}$	Before 2 min	4
$I_{Q1} > I_{Q,10min}$ and $I_{Q2} \leq I_{Q,2min}$	Between 2 and 10 min	3
$I_{Q1} \leq I_{Q,10min}$ and $I_{Q2} > I_{Q,12min}$	Between 10 and 20 min	2
$I_{Q1} \leq I_{Q,10min}$ and $I_{Q2} \leq I_{Q,12min}$	No flashover within 20 min	1
Material fails to ignite or attain a heat release rate of 50 kW/m ²	No flashover within 20 min	1

Statement:

This report was valid to test the particular material or system in the cone calorimeter for the assignment of NCC group number.

Photo Appendix:



SGS authenticate the photo on original report only

Remark: This test report is issued based on the modification of the original No. SDFTS25008205R01_EN test report issued on Jan 06,2026. And the original report is still valid. According to applicant's requirements, following changes are included:

- a. Change of applicant's name.
- b. Change of applicant's address.

End of Report



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <https://www.sgs.com/en/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

1-2/F, Building 1, European Industrial Park, No.1, Shunhe South Road, Wusha, Daliang, Shunde District, Foshan, Guangdong, China 528300
 中国·广东·佛山市顺德区大良街道办事处五沙社区居民委员会顺和南路1号欧洲工业园一号厂房首层、二层 邮编: 528300

t (86-757) 22805888 www.sgs.com.cn
 t (86-757) 22805888 sgs.china@sgs.com